

# Taktika J

Filler for joints and corners



- Firm and elastic
- Adheres well to the surface
- Ready to use
- Water-based
- Environment and health friendly

## USE

For joint tape and corner profiles application.

## SURFACE PREPARATION

The surface must be dry, capable of withstanding loads, stable and clean, primed with IGIS AG. Carefully prime the gaps.

### PLASTERBOARD JOINTS FINISHING

Stir well before use. Fill in the joint of gypsum board, immediately apply joint tape, then squeeze out the excess filler and level. When the filler dries, refill the joint if necessary. Apply smoothing layer only when the joint is completely dry.

Work tools:	spatula
Tool cleaning:	with water
Application conditions:	+10 °C to +25 °C and 35-80 % relative humidity
Coverage rate:	~0,2-0,3 l/m. The exact coverage rate is determined by covering the test area.
Drying time (23 °C, 50 % RH):	1 mm dries in 2-4 hours and gains full strength in 28 days. Drying time depends on surface, layer thickness, air temperature and humidity, etc.

## WASTE MANAGEMENT

Do not pour into drains, water or soil. Empty, dry product package should be recycled or disposed of in accordance with national law.



## TECHNICAL DATA

Purpose:	for interior use, dry areas
Binder:	acrylic copolymer
Filler:	dolomite, perlite
Solvent:	water
Color:	white, yellow white
Density:	1,62-1,63 g/cm <sup>3</sup> EN ISO 2811-1
Particle size:	<0,200 mm
pH:	8,0-9,0
Quality standards and certificates:	CE marking EN 15824, EN 13963
Volatile organic compounds (VOC):	<1 g/l EN ISO 11890-2
Non-volatile-matter content by volume:	49±1 % EN ISO 3251
Reaction to fire:	A2-s1,d0 EN 13501-1
Adhesion:	>0,3 MPa EN 13963
Shelf life in tightly closed original packaging:	1 year from the date of manufacture
Storage and transportation conditions:	store the product tightly closed in dry well-ventilated place at a temperature of +5 °C to +30 °C, protect against from damage, frost and direct sunlight.
Packing:	Taktika J 1 l, 3 l, 10 l buckets

## ADDITIONAL INFORMATION

The information above is based on laboratory tests and practical experience, and has been validated from the date indicated on the product data sheet. The manufacturer reserves the right to make technical changes. The manufacturer is not liable for damage caused by using the product not in accordance with the instructions or for improper purposes.

## MANUFACTURER

Sole Proprietorship of I. Krisciunas "IGIS", Tinklu St. 33-1, Panevezys, Lithuania  
+370 684 72323  
www.igis.lt

