

Purpose: for interior use

Binder: acrylic copolymer

Solvent: water

Color: white or tinted by color cards

Density: 1,83-1,98 g/cm³

pH: 8,3-9,3

Volatile organic compounds (VOC): <8,0 g/l EN ISO 11890-2

Volume solids: 61,5 -71,0 % (depending on the plaster type)

Adhesion (after 28 days): ≥0,3 MPa EN 1542

Work tools: grinder, spatula, airless spraying gun

Tool cleaning: with water

Application conditions: +10 °C to +25 °C and 35–80 % relative humidity

Coverage rate: 1,5-2 kg/m², the exact coverage rate is determined by covering the test area

Drying time (20 °C, 65 % RH): 24 hours. The plaster dries completely and withstands the load in 2-3 days.

Surface preparation

The surface must be dry, withstanding loads, stable and clean. Prime the surface with IGIS TEX.

Plastering

Stir well before and during use. Apply a layer of plaster to a thickness equal to the size of the largest grains and smooth. When the plaster does not stick to the tool, smooth the surface with a polyurethane plate or plastic plate for the desired texture. Avoid draught while the plaster hardens.

Precautionary statements: keep out of reach of children, avoid release to the environment, wear protective gloves/ protective clothing/eye protective/face protective. IF ON SKIN: wash with plenty of soap and water. IF IN EYES: rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

Additional hazard information: EUH208 – contains a mixture of 5-chlor-2-metil-2H-izotiazol-3-one and 2-metil-2H-izotiazol -3-one (3:1), 1,2-benzisothiazol-3(2H) -one, can cause allergy in humans.

Shelf life in tightly closed original packaging: 24 months from the date of manufacture

Storage and transportation conditions: store the product tightly closed in dry well-ventilated place at a temperature of +5 °C to +30 °C, protect against from damage, frost and direct sunlight.

Waste management: do not pour into drains, water or soil. Empty, dry product package should be recycled or disposed of in accordance with national law.

Packing: 17 kg buckets